

DTF GLITTER

FOR LIGHT & DARK COLORED GARMENTS



PRINT

Before Printing:

1. Use Latex gloves. Finger prints can affect the print quality. Keep the surface clean and free from dust.
2. Print on the coated/rough side of the film.

Printer Settings:

3. Follow the recommended DTF printer or RIP software settings.



Hot Melt Powder & Curing:

4. Apply hot melt powder & cure the transfer according to the instructions of the manufacturer.

Attention! Ovens: max 135°C (275°F) / Shaker (with Infrared-heating elements): max 100°C (212°F)



PRESS YOUR TRANSFER

Press your transfer with the parameters indicated in the table below. FOREVER DTF Glitter is a **WARM/COLD PEEL** (remove the garment from the press and then peel warm or cold).

	TEMP	TIME	PRESSURE	FIXING
COTTON	150°C / 302°F	10-15 sec.	2 Bar / 29 PSI / Medium	30 sec. / 3 Bar / 43 PSI / Medium-High
POLYESTER	135°C / 275°F	10 sec.	2 Bar / 29 PSI / Medium	30 sec. / 3 Bar / 43 PSI / Medium-High



WASH INSTRUCTIONS:

- Depending on hot melt powder and ink up to 40°C / 104°F (cold wash cycle).
- The colors become even more vibrant after the first wash.
- Turn garments inside out before washing.
- Do not use fabric softener or liquid detergents.
- **Do Not Tumble Dry.** Hang-dry or line-dry recommended.
- When ironing cover the print with baking paper or turn the garment inside out.

IMPORTANT INSTRUCTIONS

- Before commencing mass production, we strongly advise conducting print and wash tests on all materials.
- Double-Sided Printing on Textiles:
 - When printing designs on both the front and back of t-shirts, ensure that the garment is positioned over the heating plate of your transfer press. This ensures that only one side of the textile is exposed to heat, preventing any unintended alteration of the initially applied design.